

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **04081243 A**

(43) Date of publication of application: **13.03.92**

(51) Int. Cl. **B22C 1/00**
C08J 9/04
C08J 9/36
// C08L 61:06

(21) Application number: **02194388**

(22) Date of filing: **23.07.90**

(71) Applicant: **mitsui petrochem ind ltd**

(72) Inventor: **KATSURA SHINRO**

(54) MOLD MATERIAL FOR CASTING MOLTEN METAL

(57) Abstract

PURPOSE: To provide a mold material for casting molten metal having easy working and being suitable to trial production by using carbon porous body carbonizing phenol resin foam body and having the specific value of bulk density as the mold material.

CONSTITUTION: The creamy phenol resin prepolymer composition, obtd. by mixing and stirring raw material composed of resol type phenol resin, foaming agent and

hardening agent, etc., at once or in serial, is foamed and hardened and burnt at $\approx 600^{\circ}\text{C}$ and desirably $\approx 900^{\circ}\text{C}$ under non-oxidizing or slightly oxidizing atmosphere. The burning temp. can do at $\approx 1800^{\circ}\text{C}$. The carbon porous body obtd. in such way is in the range of $0.1\text{-}0.8\text{g/cm}^2$ the bulk density to obtain the excellent mold material for casting the molten metal. By this invention, a thin casting product having excellent dimensional accuracy and casting surface and little internal stress can be manufactured.

COPYRIGHT: (C)1992,JPO&Japio